


IN THE UNITED STATES PATENT AND TRADEMARK

Box New Patent Application Assistant Commissioner for Patents Washington, D.C. 20231



FILING TRANSMITTAL

Transmitted herewith for filing is the Patent Application of: Pocker et al.

For: "ENERGY GRADIENT ION BEAM DEPOSITION OF CARBON OVERCOATS ON RIGID DISK MEDIA FOR MAGNETIC RECORDINGS"

ENCLOSURES

X	19 page application including specification, claims and abstra	act:					
X	2 sheets (Figs. 1 - 6) of ⊠ informal/□ formal drawings;						
X	A Declaration, Power of Attorney & Petition (□ signed/□ u	nsigned);					
\boxtimes	A postcard for return to us as proof of receipt of the reference	• //					
	and						
X	An Assignment of the invention with an assignment cover sh	neet;					
	Verified Statement Claiming Small Entity Status (37 CFR 1.9 IDS (form PTO-1449) and copies of references;	θ(f) and 1.27(b));					
	· · · · · · · · · · · · · · · · · · ·						
	A certified copy of the priority document (Under 35 USC 11	9);					
	A Power of Attorney by Assignee;						
	Other.						
	TYPE OF FILING						
	This application claims the benefit of an earlier filed U.S. Par 120).	tent Application (35 USC					
	This application claims the benefit of the priority date of an eapplication (35 USC 119).	earlier filed provisional patent					
	This is an application filed pursuant to 37 CFR 1.53, permitti upon filing of specification, claims and drawings, if required	, with applicant being given a					
তো	period of one month from the date of notice to file the fee and						
X	In the event any parts of this application are missing, please t	reat this as a filing under					
	37 CFR 1.53 as defined just above. CERTIFICATE OF MAILING (37 CFR 1.10(A))						
ERTIFICATE OF MAILING BY "EXPRESS MAIL" - Rule 10: I hereby certify that this correspondence is being deposited with the U. S. ostal Service "Express Mail Post Office to Addressee" under 37 CFR 1.10 as Express Mail No. EL654882455US addressed to the Assistant commissioner for Patents, Washington, D.C. 20231 on November 21, 2000 by Patricia Beilmann.							
rate: November 21, 2000 Patricia Belron							

FEE CALCULATION

The filing fee has been calculated as shown below:

				SMALL EN	TITY	OR	OTHER TH SMALL EN	
BASIC FEE Design Patent				\$160	\$		\$320	\$
BASIC FEE Utility Patent				\$355	\$		\$710	\$710
EXTRA FEES				RATE	FEE		RATE	FEE
Total claims	26	minus 20 =	6	x9 =	\$0		x18 =	\$108
Independent Claims	4	minus $3 =$	1	x40 =	\$0		x80 =	\$80
Multiple Dep. Claim				+130 =	\$		+260 =	\$
■ Assignment				+40 =	\$		+40 =	\$40
☐ Rule 53 Surcharge				+65 =	\$		+130 =	\$
TOTAL					\$			\$938

FEE PAYMENT

×	Attached is Check No. 124 <u>67</u> in the sum of \$938.00 to cover the filing fee. Please charge Account No. 02-3964 the sum of \$			
	FEE DEFICIENCY			
	Please charge Account No. 02-3964 in the sum of \$			
☐ The Commissioner is authorized to charge (or credit any overpayment) to depo No. 02-3964:				
	 □ Any additional filing fees required under 37 CFR 1.16, except Rule 53 filings which will be paid within the time permitted by PTOL 1533. □ Assignment Recordal fees. 			
X	The filing fee and surcharge under 37 CFR 1.16, patent application processing fees under 37 CFR 1.17 and patent issue fees under 37 CFR 1.18 are intended to be paid by our firm as they arise. As no abandonment is intended by any inadvertent nonpayment of fees, the Commissioner is hereby authorized to charge payment of such fees as from time to time come due, if not paid prior to due date to our Deposit Account No. 02-3964.			
	A duplicate copy of this sheet is enclosed.			
Dated	l: November 21, 2000			
	Respectfully submitted,			
	Justo Sell			
	ROBERT O. GUILLOT			

LP Reg. No: 28,852

OPPENHEIMER WOLFF & DONNELLY LLP

Customer No. 25696 1400 Page Mill Road Palo Alto, CA 94304 Tel: (650) 320-4000

Attorney Docket No.: SJO990197US1 PATENT FILING TRANSMITTAL

Specification

ENERGY GRADIENT ION BEAM DEPOSITION OF CARBON OVERCOATS ON RIGID DISK MEDIA FOR MAGNETIC RECORDINGS

BACKGROUND OF THE INVENTION

5 Field of the Invention:

The present invention relates generally to protective layers fabricated upon magnetic layers of hard disk media, and more particularly to thin film diamond-like carbon protective layers.

Description of the Prior Art:

Standard magnetic media hard disks include a magnetic layer that is covered by a protective overcoat layer. The overcoat layer is necessary to provide both mechanical and corrosion protection for the magnetic layer, and typical prior art overcoat layers are composed of a hard, carbon based composition that is applied by a magnetron sputtering technique to a thickness of approximately 50 to 200 Å.

The ongoing efforts to increase the areal data storage density of magnetic disks have resulted in a need to reduce the thickness of the overcoat layer while increasing the hardness, or density of the overcoat layer. It has been found that a typical magnetron sputtered overcoat of below approximately 50 Å is not sufficiently hard, nor does it provide sufficient corrosion protection to the magnetic layer, due to the generally low energy (approximately 10 eV) at which the carbon atoms are deposited. Efforts to create a thin, hard, corrosion resistant overcoat have therefore been directed towards fabrication devices such as mass selected ion beam deposition (MSIB), cathodic arc, laser plasma deposition and plasma enhanced chemical vapor deposition

5

4

(PECVD) which produce carbon atom deposition energies of 100 eV or more. While such 100 eV deposited overcoat layers provide good mechanical and corrosion resistance properties, they also create deterioration problems for the underlying magnetic layer. Specifically, at such high energies, the carbon atoms, as well as other atoms such as nitrogen and hydrogen that are often utilized in forming the overcoat layer, become implanted into the magnetic layer to a significant depth. The implanted atoms can seriously degrade the magnetic properties of the magnetic layer within its upper regions, thus resulting in degraded performance of a magnetic disk that is fabricated with an overcoat layer formed with prior art high energy carbon deposition techniques.

The present invention solves these prior art problems through the use of an energy gradient ion beam deposition technique in which the implanting of carbon overcoat ions into the magnetic layer is reduced.

SUMMARY OF THE INVENTION

In the energy gradient ion beam deposition technique of the present invention, the fabrication of the overcoat layer starts with a low energy ion beam to avoid magnetic layer implantation problems, followed by higher deposition energies where the higher energy atoms are implanted into the previously formed lower energy overcoat layer, rather than the magnetic layer. The energy gradient ion beam deposition process therefore results in a thin overcoat layer that is denser than a comparable layer formed by low energy magnetron sputtering, and which overcoat layer provides good mechanical and corrosion protection to the magnetic layer, without degrading the magnetic properties of the magnetic layer. Where a magnetic media hard disk of the present invention is utilized within a hard disk drive, the thinner overcoat layer allows the magnetic head of the disk drive to fly closer to the magnetic media layer, thereby facilitating an increase in the areal data storage density of the hard disk drive.

5

It is an advantage of the magnetic media hard disk of the present invention that it is fabricated with a thinner overcoat layer.

It is another advantage of the magnetic media hard disk of the present invention that it is fabricated with a denser overcoat layer.

It is a further advantage of the magnetic media hard disk of the present invention that it is fabricated with a thinner, denser effective overcoat layer wherein minimal implantation of carbon ions into the magnetic media layer is found.

It is yet another advantage of the magnetic media hard disk of the present invention that it is fabricated with a thinner effective overcoat layer such that a greater areal data storage density can be created with said disk.

It is an advantage of the magnetic media hard disk drive of the present invention that it includes one or more magnetic media hard disks of the present invention wherein the data storage within said disk drive is increased.

It is another advantage of the hard disk drive of the present invention that it includes one or more magnetic disks of the present invention having a thinner effective overcoat layer, such that the areal data storage density of said hard disk drive may be increased.

It is an advantage of the fabrication process for a magnetic media hard disk of the present invention that a thinner, denser overcoat layer is fabricated with minimal carbon ion implantation into a magnetic media layer of the hard disk.

It is another advantage of the fabrication process for a magnetic media hard disk of the present invention that controlled deposition of nitrogen ion species into the overcoat layer may be accomplished.

5

These and other features and advantages of the present invention will no doubt become apparent to those skilled in the art upon reading the following detailed description which makes reference to the several figures of the drawings.

IN THE DRAWINGS

- Fig. 1 is a side cross-sectional view depicting a prior art overcoat layer formed by magnetron sputtering fabrication techniques;
- Fig. 2 is a side cross-sectional view of a prior art magnetic disk including an overcoat layer that is formed utilizing high energy carbon ion beam fabrication techniques;
- Fig. 3 is a graphical representation of the implantation of carbon ions of various energy levels into a magnetic layer;
- Fig. 4 is a side cross-sectional view depicting a magnetic disk having an overcoat layer that is fabricated utilizing the energy gradient ion beam deposition technique of the present invention;
- Fig. 5 is a graphical representation of the implantation of 100 eV carbon ions into 20 Å carbon surface layers having different densities; and
- Fig. 6 is a schematic top plan view of a hard disk drive including the magnetic disk of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As is well known to those skilled in the art, a thin film overcoat layer is fabricated upon the magnetic layer of a magnetic media hard disk to provide mechanical and corrosion protection to the magnetic layer. Fig. 1 is a side cross-sectional view of a typical prior art magnetic media hard disk 10 having such an overcoat. As depicted in Fig. 1, the prior art hard disk 10 includes a disk substrate 14 that typically has a plurality of thin film layers deposited thereon. While

5

various types of prior art hard disks exist, with various numbers and compositions of thin film layers, for the purposes of this disclosure, a typical prior art hard disk 10 can be said to include a at least one underlayer 18 formed upon the surface of the substrate 14, a magnetic layer 26 formed upon the underlayer 18, and an overcoat layer 30 formed upon the magnetic layer 26. As indicated above, the present invention is directed to the features and relationships between the magnetic layer 26 and the overcoat layer 30. In a typical prior art hard disk 10, the magnetic layer 26 is composed of a magnetic material, usually having a CoPtCr composition, that has a thickness of approximately 50 to 200 Å. The overcoat layer 30 is composed of diamond-like carbon (DLC) and is applied utilizing a magnetron sputtering technique having a relatively low application energy that is less than or equal to approximately 10 eV, and the DLC layer 30 is deposited to a thickness of at least approximately 50 Å to 200 Å. It is significant that there is very little implantation of the sputtered carbon ions of the overcoat layer 30 into the magnetic layer 26, due to the low ion energy level of the overcoat layer fabrication technique.

To increase the hard disk data areal storage density, it is desirable to write magnetic data bits closer together in the data track; that is, to increase the number of bits per inch (BPI). To accomplish this, it is desirable to have the magnetic write head positioned closer to the magnetic layer, and decreasing the thickness of the overcoat layer 30 is advantageous in this regard. However, it has been found that if the thickness of the prior art low energy magnetron sputtered overcoat layer 30 is reduced to below approximately 50 Å, both the mechanical protection and corrosion protection of the magnetic layer is 25 adversely affected. A prior art approach to resolve this problem is to apply the overcoat layer 30 utilizing a higher energy ion beam fabrication technique, such that a denser overcoat layer is fabricated than is achieved in the low energy magnetron sputtering process. Where the overcoat layer is denser, a thinner layer will

5

provide suitable mechanical and corrosion protection to the magnetic layer, and a magnetic hard disk 50 with such a prior art high deposition energy DLC overcoat layer is depicted in Fig. 2.

As depicted in Fig. 2, the prior art magnetic hard disk 50 includes a substrate 14 upon which an underlayer 18 has been deposited, followed by a 200 Å thick magnetic layer 26. The layers 14, 18 and 26 may be identical to those described above with regard to prior art hard disk 10, whereby identical identification numbers are used herein. A DLC overcoat layer 54 that is fabricated in a high energy fabrication process such as mass selected ion beam deposition (MSIB), cathodic arc, laser plasma deposition and plasma enhanced chemical vapor deposition (PECVD) is formed upon the magnetic layer 26. It has been observed that some of the high energy carbon ions that form the overcoat layer 54 penetrate into the magnetic layer 26, forming an ion implanted upper portion 58 of the magnetic layer of approximately 10 Å to 20 Å, as shown by the cross hatched portion 58 of the magnetic layer 26.

A graphical representation of the implantation of carbon ions of various energy levels into a magnetic layer is presented in Fig. 3. More specifically, Fig. 3 depicts an implantation profile 70 for 10 eV carbon ions, wherein the vertical axis (I/I₀) represents the quantity of carbon ions and the horizontal axis represents the implantation depth of the carbon ions from the surface (zero) into the magnetic media layer which is composed of a CoPtCr alloy. In like manner, graphical profile 74 represents 50 eV carbon ions, graphical profile 78 represents 100 eV carbon ions and graphical profile 82 represents 500 eV carbon ions. As is seen in Fig. 3, the great majority of 10 eV carbon ions 70 are deposited within the first 5 Å, and nearly all of the 10 eV carbon ions are deposited within the first 8 Å of the magnetic layer. With regard to 100 eV carbon ions 78, a significant portion thereof are deposited in excess of 10 Å. Thus, the

5

crosshatched portion 58 of magnetic layer 26 of Fig. 2 may be generally as deep as 20 Å for the 100 eV carbon ions.

Significantly, the implanted carbon ions influence the magnetic properties of the magnetic layer portion 58 and degrade its performance. The degraded performance of the ion implanted upper portion 58 of the magnetic layer can be quite significant with regard to overall disk performance, because the upper portion 58 of the magnetic layer 26 contributes significantly to the performance characteristics of magnetic data bits that are written into the magnetic layer. Therefore, the high energy overcoat layer 54 is thinner than the prior art low energy magnetron sputtered layer 30, while still providing good hardness and corrosion resistance; but the magnetic performance properties of the hard disk 50 are somewhat degraded due to the implantation of carbon overcoat layer ions into the magnetic layer 26. The present invention provides an improvement in the prior art overcoat layer technologies by utilizing an ion deposition beam having an energy gradient, such that carbon ion implantation into the magnetic layer is minimized, while the desired thinness and density of the DLC overcoat layer are achieved.

As depicted in Fig. 4, a magnetic media hard disk 100 of the present invention generally includes the substrate 14, underlayer 18 and magnetic layer 26, as are generally known in the prior art and described hereabove with regard to Figs. 1 and 2 above, and a DLC overcoat layer 108 of the present invention that is fabricated on top of the magnetic layer 26. In that the present invention relates generally to the DLC overcoat layer 108, magnetic media hard disks having other, different and additional layers fabricated beneath the magnetic layer 26, as well as various magnetic layer compositions are intended to be included within the scope of the present invention.

5

As has been indicated above, the overcoat layer 108 of the present invention is thinner and denser than the low energy magnetron sputtered layer 30, and it is fabricated such that carbon ion implantation into the magnetic layer 26 is minimized. To accomplish this, the overcoat layer 108 is fabricated utilizing a device that produces an ion beam that has an ion deposition energy gradient. Specifically, the fabrication of the overcoat layer 108 is commenced with the deposition of an initial overcoat layer portion 112 with a low energy ion beam, such as a 10 to 20 eV ion beam, which is generally the energy level of the low energy magnetron sputtering process of the prior art, as depicted in Fig. 1. Thereafter, as the deposition of the initial overcoat layer portion 112 progresses, the overcoat layer 112 increases in thickness upon the surface of the magnetic layer 26, and due to the relatively low deposition beam energy level, implantation of overcoat layer ions into the magnetic layer 26 is minimized. After the initial overcoat layer thickness is deposited at the low energy level, the energy level of the beam is increased to deposit an intermediate overcoat layer portion 116. The higher energy ions will penetrate more deeply into the surface layer, as has been described hereabove with regard to prior art disk 50; however, because the initial surface layer 112 has been formed of overcoat material, the higher energy overcoat ions penetrate only into the pre-existing initial overcoat layer portion 112. Thus, as the build up of the intermediate overcoat layer portion 116 progresses, the total overcoat layer generally both becomes thicker with overcoat ions that remain on its surface, as well as denser with higher energy overcoat ions that become implanted within the thickness of the initial overcoat layer. Thereafter, a subsequent overcoat layer portion 118 may be deposited with a still higher ion beam energy level. Again, these higher energy overcoat ions penetrate into the surface of the overcoat layer 108. However, due to the thickness of the existing overcoat layer the high energy ions become implanted into both the initial and

5

intermediate overcoat layer portions and do not penetrate into the magnetic layer 26. A typical DLC overcoat layer density of the present invention is between approximately 2.0 g/cm³ to approximately 2.9 g/cm³.

Fig. 5 is a graphical representation of 100 eV carbon ion implantation into a magnetic disk having surface layers deposited thereon. Specifically, the graphical profile 120 represents the implantation of 100 eV carbon ions into a CoPtCr magnetic layer having no surface layer deposited thereon, and it can be seen that profile 120 is substantially identical to profile 78 of Fig. 3. Profile 124 represents the 100 eV carbon ion implantation into a 20 Å aC:H surface layer having a density of 1.7 grams/centimeter. It can be seen that the great majority of the 100 eV carbon ions are deposited within the 20 Å depth of the surface layer. Graphical profile 128 represents the implantation of 100 eV carbon ions into a 20 Å IBD-C surface layer having a density of 2.2 grams/centimeter, wherein it is seen that nearly all of the 100 eV carbon ions are implanted within the 20 Å IBD-C surface layer. It is therefore to be understood from the graphical representations of Fig. 5 that a sufficiently dense surface layer will prevent the implantation of 100 eV carbon ions into the magnetic layer of a hard disk.

It is therefore to be generally understood that the energy gradient of the ion beam is to be controlled in association with the thickness of the overcoat layer that is being fabricated, such that the highest beam energy levels are utilized when the thickness of the overcoat layer is close to its desired thickness. In this ion beam energy gradient fabrication process the higher energy ions become predominantly implanted into the pre-existing overcoat layer portion, thereby increasing its density, hardness and corrosion resistance, without adding significantly to its thickness, and implantation of ions into the magnetic layer is minimized. Additionally, it is known that the addition of nitrogen ions into the DLC layer can have a positive effect upon its

5

hardness and corrosion resistance. However, nitrogen ions can also create significant problems if they become implanted into the magnetic layer. Therefore, in an alternative preferred embodiment of the present invention, the initial lower energy overcoat layer fabrication is conducted without nitrogen ions. Thereafter, when an initial low energy overcoat layer has been deposited, nitrogen ions are then included within the higher energy ion beam, to also become implanted within the overcoat layer, rather than into the magnetic layer. A nitrogen enhanced DLC layer is thereby produced in which nitrogen ion implantation into the magnetic layer is minimized.

The present invention has been implemented in a Circulus magnetic media hard disk fabrication device. In this device, the DLC overcoat layer is applied onto the magnetic layer of hard disks utilizing a radio frequency (RF) discharge chamber, which creates an overcoat ion plasma from a gaseous source. In this device, a deposition rate of approximately 10 Å per second is achieved with appropriate input gas concentrations and other control parameters as are well known to those skilled in the art.

To create a DLC overcoat layer of the present invention, acetylene gas was utilized as the carbon ion source. The chamber control parameters were set such that the acetylene gas produced a carbon ion plasma that was directed to the magnetic layer of a hard disk disposed within the chamber. The disk was exposed to an ion beam energy of approximately 10 eV for approximately one second, resulting in an initial carbon overcoat layer having a thickness of approximately 10 Å. Thereafter, the ion beam energy level was increased to approximately 50 eV and the disk was exposed for an additional one second to add an intermediate overcoat layer portion 116, to create an overcoat layer having a thickness of approximately 19 Å. Thereafter, the ion beam energy was increased to approximately 100 eV, and the disk was exposed to the ion

5

beam for approximately one second, to produce a subsequent overcoat layer portion 118, such that the total overcoat layer 108 has a thickness of approximately 25 Å. In an enhanced overcoat layer deposition process, nitrogen gas can be mixed with the acetylene gas in the second and third deposition energy level steps to create nitrogen ions that are implanted into the overcoat layer. The concentration of nitrogen can be increased as the energy level is increased to create a nitrogen enhanced overcoat layer. A preferred concentration range of nitrogen ions within the overcoat layer is from approximately 2 at. % to approximately 20 at. %.

While the example provided hereabove demonstrates the use of a three step (10 eV, 50 eV, 100 eV) ion beam energy gradient, it is to be understood that the present invention can be practiced utilizing a two step gradient, a multiple step gradient, and a smooth energy gradient. Additionally, ion beam energy levels in excess of 100 eV are contemplated, although there appears to be little advantage to ion beam energy levels in excess of approximately 100 eV. A general principal of the present invention is that the thickness of the DLC layer formed at lower energy levels be sufficient to capture the carbon and nitrogen ions that become implanted at higher energy levels. With the use of appropriate process parameters such as deposition rates and times, as will be understood by those skilled in the art after having read this disclosure, the thickness and density of the overcoat layer can be controlled. Preferred embodiments of the present invention have an overcoat thickness of from approximately 25 Å to approximately 100 Å, with a more preferred upper thickness range of approximately 60 Å, and with a more preferred thickness of approximately 35 Å; the density of the overcoat is between approximately 2.0 g/cm³ to 2.9 g/cm³, and the optional nitrogen concentration is from 2 at. % to 20 at.%

The magnetic disk of the present invention is designed for installation in a hard disk drive, and Fig. 6 is a schematic top plan view of a hard disk drive 200 which includes at least

one, and typically a plurality, of magnetic disks 100 of the present invention. As depicted therein, at least one magnetic head disk 100 is rotatably mounted upon a motorized spindle 204. A slider 208, having a magnetic head 212 disposed thereon, is mounted upon an actuator arm 216 to fly above the surface of each rotating hard disk 100, as is well known to those skilled in the art. The hard disk drive 200 of the present invention thus includes improved features and manufacturing methods for the magnetic disk 100 as have been described hereabove.

While the present invention has been shown and described with reference to certain preferred embodiments, it is to be understood that those skilled in the art will no doubt devise certain alterations and modifications thereto which nevertheless include the true spirit and scope of the present invention. It is therefore intended that the following claims cover all such alterations and modifications in form and detail that nevertheless include the true spirit and scope of the present invention.

What we claim is:

CLAIMS

_	_		. •	4.	1 1		
1	1	Λ		*** A di 1 A	4040	diant	comprising:
1		AI	пяопенс	шеша	пан	HINK	COHIDITSHIY.
1	1,	1 2 2	uuzuvuv	mound	11th G	GIDIL,	OCIMPITOTING.

- a substrate; 2
- 3 a magnetic layer;
- at least one underlayer being disposed between said substrate and said magnetic layer; 4
- an overcoat layer being disposed above said magnetic layer, said overcoat layer being 5
- comprised of diamond-like carbon (DLC), and wherein carbon atoms of said DLC layer are 6
- generally implanted into said magnetic layer to a depth of less than approximately 10 Å, and 7
- wherein the density of said overcoat layer is between approximately 2.0 g/cm3 and 8
- approximately 2.9 g/cm³.
 - 2. A magnetic disk as described in claim 1 wherein the thickness of said overcoat layer is
- from approximately 25 Å to approximately 100 Å.
 - A magnetic disk as described in claim 1 wherein the thickness of said overcoat layer is 3.
- from approximately 25 Å to approximately 60 Å.
 - A magnetic disk as described in claim 1 wherein the thickness of said overcoat layer is 1 4.
 - approximately 35 Å. 2
 - 5. A magnetic disk as described in claim 1 wherein said overcoat layer includes nitrogen. 1

- 1 6. A magnetic disk as described in claim 5 wherein said overcoat layer includes nitrogen in
- 2 the range of approximately 2 at. % to approximately 20 at. %.
- 1 7. A hard disk drive, comprising:
- 2 at least one magnetic media hard disk being adapted for rotary motion upon a disk drive
- 3 motor spindle;
- 4 at least one slider device having a slider body portion being adapted to fly over said
- 5 magnetic media hard disk;
- 6 a magnetic head being formed on said slider body for writing data to said magnetic media
- **17** hard disk and reading data from said magnetic media hard disk;
- 8 9 10 said magnetic media hard disk, including:
 - a substrate;

<u>F</u>

13

- a magnetic layer;
- . .11 at least one underlayer being disposed between said substrate and said magnetic layer;
- 12 an overcoat layer being disposed above said magnetic layer, said overcoat layer being FLI
 - comprised of diamond-like carbon (DLC), and wherein carbon atoms of said DLC layer are
- generally implanted into said magnetic layer to a depth of less than approximately 10 Å, and 14
- 15 wherein the density of said overcoat layer is between approximately 2.0 g/cm³ and
- 16 approximately 2.9 g/cm³.
- 1 A hard disk drive as described in claim 7 wherein the thickness of said overcoat layer is 8.
- 2 from approximately 25 Å to approximately 100 Å.

- 1 9. A hard disk drive as described in claim 7 wherein the thickness of said overcoat layer is
- 2 from approximately 25 Å to approximately 60 Å.
- A hard disk drive as described in claim 7 wherein the thickness of said overcoat layer is 1 10.
- 2 approximately 35 Å.
- 1 11. A hard disk drive as described in claim 7 wherein said overcoat layer includes nitrogen.
- 1 A hard disk drive as described in claim 11 wherein said overcoat layer includes nitrogen 12. ₽2 in the range of approximately 2 at. % to approximately 20 at. %.
 - 13. A process for fabricating a magnetic media hard disk comprising the steps of:
- fabricating a magnetic media layer upon a surface material of a substrate:
- fabricating a diamond-like carbon (DLC) layer upon said magnetic layer, including the <u>.</u> 4 steps of: # Lg
 - fabricating an initial thickness DLC layer portion upon said magnetic layer utilizing a relatively low ion carbon beam energy;
 - 7 fabricating a subsequent thickness DLC layer portion upon said initial thickness
 - 8 DLC layer portion utilizing a relatively high carbon ion beam energy.
 - A process for fabricating a magnetic media hard disk as described in claim 13 wherein 1 14.
 - 2 said relatively low carbon ion beam energy is approximately 10 eV to approximately 20 eV.

11 6

- 1 15. A process for fabricating a magnetic media hard disk as described in claim 14 wherein
- 2 said relatively high ion beam energy is approximately 100 eV.
- 1 16. A process for fabricating a magnetic media hard disk as described in claim 13, including
- 2 the further step of fabricating an intermediate thickness DLC layer portion between said initial
- 3 DLC layer portion and said subsequent DLC layer portion, wherein said intermediate thickness
- 4 DLC layer portion is fabricated utilizing a relatively mid-range carbon ion beam energy between
- 5 said relatively low carbon ion beam energy and said relatively high carbon ion beam energy.
- A process for fabricating a magnetic media hard disk as described in claim 16 wherein 17.
 - said intermediate carbon ion beam energy is approximately 50 eV.
 - 18. A process for fabricating a magnetic media hard disk as described in claim 17 wherein
 - said DLC layer has a thickness of approximately 10 Å following the deposition of said initial
 - thickness DLC layer portion, and said DLC layer has a thickness of approximately 19 Å
 - following the deposition of said intermediate thickness DLC layer portion, and said DLC layer
 - has a final thickness of approximately 25 Å following the deposition of said subsequent 5
 - 6 thickness DLC layer portion.

T. 4

- 1 19. A method for fabricating a magnetic media hard disk as described in claim 18 wherein
- said DLC layer is formed with a density of approximately 2.0 g/cm³ to approximately 2.9 g/cm³. 2

- 1 20. A method for fabricating a magnetic media hard disk as described in claim 13 wherein
- 2 nitrogen ion species are deposited within said subsequent thickness DLC layer portion.
- 1 21. A process for fabricating a magnetic media hard disk as described in claim 20 wherein
- 2 said nitrogen species are deposited in a range of approximately 2 at. % to approximately 20 at.
- 3 %.

8

1 9

10


- 1 22. A method for fabricating a magnetic media hard disk comprising the steps of:
- 2 fabricating a magnetic material layer upon a material surface of a substrate;
 - fabricating a diamond-like carbon (DLC) layer upon said magnetic layer, wherein said DLC layer is fabricated in the steps of:
 - depositing carbon ion species upon said magnetic layer utilizing a relatively low carbon ion beam energy of from approximately 10 eV to approximately 20 eV, to deposit an initial DLC layer thickness;
 - subsequently increasing the carbon ion beam energy level as the thickness of said DLC layer increases due to deposition of carbon ion species within said DLC layer, such that higher energy carbon ion beam species become implanted within said DLC layer thickness.
- 1 23. A method for fabricating a magnetic media disk as described in claim 22 wherein said
- 2 carbon ion beam energy level is varied smoothly with time.
- 1 24. A method for fabricating a magnetic media hard disk as described in claim 22 wherein
- 2 said carbon ion beam energy level varies as a step function with time.


- 1 25. A method for fabricating a magnetic media hard disk as described in claim 23 wherein
- 2 nitrogen ion species are implanted within said DLC layer thickness.
- 1 26. A method for fabricating a magnetic media hard disk as described in claim 25 wherein
- 2 said nitrogen ion species are included within said DLC layer in a range of approximately 2 at. %
- 3 to approximately 20 at. %.


ABSTRACT

ENERGY GRADIENT ION BEAM DEPOSITION OF CARBON OVERCOATS ON RIGID DISK MEDIA FOR MAGNETIC RECORDINGS

In the energy gradient ion beam deposition technique of the present invention, the fabrication of the overcoat layer starts with a low energy ion beam to avoid magnetic layer implantation problems, followed by higher deposition energies where the higher energy atoms are implanted into the previously formed lower energy overcoat layer, rather than the magnetic layer. The energy gradient ion beam deposition process therefore results in a thin overcoat layer that is denser than a comparable layer formed by low energy magnetron sputtering, and which overcoat layer provides good mechanical and corrosion protection to the magnetic layer, without degrading the magnetic properties of the magnetic layer. Where a magnetic media hard disk of the present invention is utilized within a hard disk drive, the thinner overcoat layer allows the magnetic head of the disk drive to fly closer to the magnetic media layer, thereby facilitating an increase in the areal data storage density of the hard disk drive.







DECLARATION, POWER OF ATTORNEY AND PETITION

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled "Energy Gradient Ion Beam Deposition of Carbon Overcoats on Rigid Disk Media for Magnetic Recordings" the specification of which

(check one)	×	is attached hereto.					
		was filed on and was amende	as Applica	ation Serial No			
		and was amende	d on	(if ap	plicable).		
I hereby state that claims, as amended by any a		ave reviewed and unded dment referred to above		ntents of the abo	ove identified spec	cification, inclu	ding the
I acknowledge the with Title 37, Code of Feder	-	to disclose information to disclose informations, § 1.56(a).	on which is ma	aterial to the exam	mination of this ap	oplication in acc	ordance
I hereby claim fo patent or inventor's certific certificate having a filing da	cate 1		also identified	d below any for	eign application f		
		Prior F	oreign Appl	ication(s)			
						Priority	Claimed
(Number)(Country)(Day, m	onth,	year filed)				Yes	No
(Number)(Country)(Day, m	onth,	year filed)				Yes	No
(Number)(Country)(Day, m	onth,	year filed)				Yes	No
I hereby claim the and, insofar as the subject m the manner provided by the information as defined in T application and the national	atter first itle 3	paragraph of Title 35, 7, Code of Federal Re	f this applicati United States gulations, § 1.	on is not disclose Code, § 112, I a .56(a) which occ	ed in the prior Uni acknowledge the d	ted States applicately to disclose	cation in material
(Application Serial No.)		Filing Date			(Status: Patente	d, pending, aba	ndoned)
(Application Serial No.)		Filing Date			(Status: Patente	d, pending, aba	ndoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

And I hereby appoint W. POMS, REG. 18,782; G.P. SMITH, REG. 20,142; G. E. LANDE, REG. 22,222; A.C. ROSE, REG. 17,047; L.J. BOVASSO, REG. 24,075; C. BERMAN, REG. 29,249; D.J. OLDENKAMP, REG. 29,421; C. DARROW, REG. 30,166; M.E. HARRIS, REG. 26,690; K.A. MACLEAN, REG. 31,118; C. ROSENBERG, REG. 31,464; M.E. BROWN, REG. 28,590; S.R. HANSEN, REG. 38,486; D.N. LARSON, REG. 29,401; J.W. INSKEEP, REG. 33,910; H.D. JASTRAM, REG. 19,777; B. CANTER, REG. 34,792; C.J. LERVICK, REG. 35,244; L. CULLMAN, REG. 39,645; C.A.S. HAMRICK, REG. 22,586; R.O. GUILLOT, REG. 28,852; J. BOYCE, REG. 40,920; C. CHOU, REG. 41,672; A.B. DIEPENBROCK, REG. 39,960; M.K. BOSWORTH, REG. 28,186, L. SHERRY, REG. 43,918; L. McROSS, REG. 40,427; E.E. KLEIN, REG. 34,337;

Docket No.: SJO990197US1

The state and and allowable the state of the state and allowable states are states and allowable states and allowable states are states and allowable states are states are

P. SABER, REG. 37,494; E.A. PENNINGTON, REG. 32,588; J.C. REDMOND, JR., REG. 18,753; R.B. MARTIN, REG. 26,945; R.J. BLUESTONE, REG. 40,518; D.R. MILLETT, REG. 31,784; C.A. HUGHES, REG. 26,914; J.E. HOEL, REG. 26,279; OPPENHEIMER WOLFF & DONNELLY LLP, 1400 Page Mill Road, Palo Alto, California 94304, (650) 320-4000, as my attorneys with full power of substitution and revocation, to prosecute said application and to transact in connection therewith all business in the Patent and Trademark Office and before competent International Authorities.

Address all telephone calls to Robert O. Guillot at (650) 320-4000, and address all correspondence to:

Robert O. Guillot, Esq. OPPENHEIMER WOLFF & DONNELLY LLP

1400 Page Mill Road Palo Alto, CA 94304

Wherefore I pray that Letters Patent be granted to me for the invention or discovery described and claimed in the foregoing specification and claims, and I hereby subscribe my name to the foregoing specification and claims, declaration, power of attorney, and this petition.

Full Name of Sole or First Inventor:	Daryl J. Pocker	_
Home Address:	1123 Petroni Way, San Jose, CA 95120	-
Post Office Address:	Same as above	-
Citizenship:	United States	- 1) (/200
Inventor's Signature:	Mylloson	Date: <u>Nov. 16, 2</u> 80
Full Name of Second Inventor:	Jan-Ulrich Thiele	-
Home Address:	806 Coleman Avenue #5, Menlo Park, CA 94025	-
Post Office Address:	Same as above	-
Citizenship:	Germany	_
Inventor's Signature:	32-4000000000000000000000000000000000000	Date: Mos. 17, 2000
Full Name of Third Inventor:	Richard L. White	_
Home Address:	928 Clinton Road, Los Altos, CA 94024	_
Post Office Address:	Same as above	_
Citizenship:	United States	_ \
Inventor's Signature:	Richard & Whit	Date: NOV 16, 2000

Full Name of Fourth Inventor:

Bing K. Yen

Home Address:

5583 Blossom Garder Circle, San Jose, CA 95123

Post Office Address:

Same as above

United States

Inventor's Signature:

Date: Nov. 17, 2000